Effect of Incorporating Pottery and Bottom Ash as Partial Replacement of Cement

Bassam A. Tayeh

The Islamic University of Gaza, btayeh@iugaza.edu.ps

Doha M. AlSaffar

Al Mansour University College, doha.mothefer@muc.edu.iq

Lawend K. Askar

Duhok polytechnic University, lawend.kamal@dpu.edu.krd

Asmahan Issa Jubeh

The Islamic University of Gaza, ajubeh@iugaza.edu.ps

Follow this and additional works at: <https://kijoms.uokerbala.edu.iq/home>

Part of the [Ceramic Materials Commons](#), [Civil Engineering Commons](#), [Other Materials Science and Engineering Commons](#), [Polymer and Organic Materials Commons](#), and the [Structural Materials Commons](#)

Recommended Citation

Tayeh, Bassam A.; AlSaffar, Doha M.; Askar, Lawend K.; and Jubeh, Asmahan Issa (2019) "Effect of Incorporating Pottery and Bottom Ash as Partial Replacement of Cement," *Karbala International Journal of Modern Science*: Vol. 5 : Iss. 4 , Article 9.

Available at: <https://doi.org/10.33640/2405-609X.1220>

This Research Paper is brought to you for free and open access by Karbala International Journal of Modern Science. It has been accepted for inclusion in Karbala International Journal of Modern Science by an authorized editor of Karbala International Journal of Modern Science.

Effect of Incorporating Pottery and Bottom Ash as Partial Replacement of Cement

Abstract

This study addressed the environmental constraints in cement production. Ordinary Portland cement (OPC) was replaced with pottery powder (PP, produced by grinding locally available pottery) and bottom ash (BA) at 10%, 20% and 30% of cement mass. Moreover, 4% calcium chloride solution ($\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$) was used as mixing water. Material properties, such as standard consistency, setting time and compressive strength, were measured with different percentages of OPC replacement with PP and BA. Results indicated that the replacement with PP and BA increased the water demand to achieve the standard consistency. These results revealed that the strength evolution of 30% PP and BA is lower than that of the corresponding OPC mix, whereas the 10% and 20% replacements have a similar compressive strength to the control mix at 28 and 90 days, respectively. Slightly higher compressive strength was observed with the addition of 4% CaCl_2 than the OPC mix.

Keywords

Pottery powder; bottom ash; calcium chloride; Eco efficient mortar; durable mortar

Creative Commons License

This work is licensed under a [Creative Commons Attribution-NonCommercial-No Derivative Works 4.0 License](https://creativecommons.org/licenses/by-nc-nd/4.0/).

1. Introduction

Cement is the most used building material worldwide. However, in environmental aspects, the cement industry is responsible for 5% of total CO₂ emissions. Environmentally friendly alternatives to cement are required to preserve the environment [1–9]. Many waste materials produced by this industry are neglected by humans. Some of these waste materials can be replaced by the weight of cement, and this technique reduces the environmental impact, construction costs, energy consumption, CO₂ emissions and the volume of waste materials. In addition, with the global attention on the political and social requirements for recycling industrial by-products and waste materials, artificial lightweight aggregates have been manufactured from various source materials, such as crushed waste clay brick (CB), pottery powder (PP), marble, glass powder and bottom ash (BA); these materials are naturally occurring products from the coal combustion process [10–19]. Using industrial by-products and waste materials is beneficial to sustainability goals, including recirculation of resources and restoration of landfill. Studies [10,16,18,20–22] have been conducted as positive actions in the concrete industry in response to the global sustainability requirements. They have regarded CB as a Pozzolanic material on the basis of the chemical analysis of clay that contains 58.4% silica and 28.7% alumina [10]. The amounts of silica and alumina in CB are 60.64% and 14.23%, respectively [16], and ground brick has a high content of SiO₂ (73.64%) and low content of CaO (1.29%) [23,24]. ASTM C618 states that for a potentially suitable Pozzolanic material, the combination of SiO₂, Al₂O₃ and Fe₂O₃ must not be less than 70% [1,21]. Thus, partial or complete use of BA and PP for producing concrete can be highly effective in preserving natural resources, such as sand, crushed rock and gravel, considering previous reports [8,24,25] emphasising that approximately 9 billion tons of natural aggregates are consumed annually by the concrete industry.

Previous studies [26–29] have indicated that the workability of concrete is kept constant when cement is replaced with 10%–20% of CB and reduced in bulk density [13,16]; however, its compressive strength has a significant improvement at 28 days compared with the control mix. They concluded that

the fineness of clay from 360 m²/kg to 420 m²/kg insignificantly increases the strength. Clay effectively reacts with the activators NaOH and KOH solutions, and compressive strength increases with age [10,29]. However, the addition of high percentages of CB slightly decreases the splitting tensile strength, and the range of tensile strength is 2–4 MPa with replacements of 10%, 20% and 30% at 28 days [13]. The flexural strength is not adversely affected by the addition of CB [23], and the flexural strength is 10–12 MPa with replacements of 10%, 20% and 30% [13].

Ge et al. [13] reported that replacing cement with CB decreases the hydration heat because CB has high water absorption and reduces the autogenous shrinkage. Given good internal curing, limited research work has been conducted on mixing cement mortar with PP and BA. Hence, the present study aims to investigate the behaviour of PP and BA as Pozzolanic materials in cement mortar. From the durability viewpoint, the effect of calcium chloride solution (CaCl₂) is also reported. On this basis, the authors seek a sustainable alternative to partially replace Portland cement, as well as to reduce the disposal of this waste in landfills.

2. Experimental investigation

2.1. Materials

In this experiment, ordinary Portland cement (OPC) with a specific gravity of 3.15 and Blaine fineness of 350 m²/kg (conforming to ASTM C150 Type I) [30] was used. Tables 1 and 2 present the chemical and physical properties of this cement. The fine aggregate was natural siliceous river sand with a saturated surface-dry specific gravity of 2.78 and absorption of 0.81%, and a fineness modulus of 2.64 was used. This material was purchased from Gaza Strip. Table 3 shows the grading. PP and BA were obtained from Gaza Strip factories. The pottery was ground in a laboratory-scale horizontal ball mill to obtain a powder. Grinding was performed until all samples passed through a No. 200 sieve (75 µm), as shown in Fig. 1 and Fig. 2 exhibits the methodology of pottery preparation. The chemical compositions of PP and BA were obtained using an X-ray diffraction, as shown in Table 1. Experiments and analysis involving SEM were considered from a previous

Table 1
Chemical compositions of cementitious materials.

	OPC ^a	BA ^a	PP ^a
CaO, %	65	8.7	10.7
SiO ₂ , %	20.6	45.3	47.6
Al ₂ O ₃ , %	4.6	18.1	23.8
Fe ₂ O ₃ , %	2.7	19.84	7.42
MgO, %	2.4	0.969	1.5
SO ₃ , %	2.1	0.352	0.759
NaO ₂ , %	0.13	—	2.16
K ₂ O, %	0.49	2.48	1.68

^a Note: OPC is ordinary Portland cement; BA is Bottom ash; and PP is pottery powder.

study [1]. Fig. 3 presents the image. In accordance with the manufacturer's recommendations of using 2%–4% of calcium chloride (CaCl₂) solution to obtain benefits and with the objectives of this investigation [31], this percentage was selected on the basis of previous work [32]. Thus, the CaCl₂ solution consisting of only one salt with 4% CaCl₂ was prepared, and the reagent grade CaCl₂·2H₂O was used to prepare a solution with extra water (adjusted CaCl₂·2H₂O), as shown in Fig. 4. Tap water in Gaza was used.

2.2. Methodology and mixture proportions

A total of 23 mortar mixtures classified into two series was tested, as presented in Tables 4 and 5. The mixture proportions of all mortar specimens for the targeted requirements were designed in accordance with ASTM C109 [33]. In the first series, the variable parameters were studied. The replacement with PP was varied at 10%, 20% and 30% of cement mass, and the replacement with BA was varied at 5%, 10%, 15%, 20% and 30% of cement mass. All mixtures

were divided into three main groups. The first group was composed of 18 binary blended mixtures incorporating PP as cement replacement at 10%, 20% and 30%. The second group was composed of 30 binary blended mixtures, incorporating BA as cement replacement at 5%, 10%, 15%, 20% and 30%. The third group was composed of 18 specimens, including three blended mixtures containing OPC, PP and BA, as illustrated in Table 5. In the second series, the effect of calcium chloride (CaCl₂) solution on the mixtures in the first series was studied. The CaCl₂ solution consisting of only one salt with 4% CaCl₂ was prepared. Mixture proportioning was performed for the M40 grade of mortar. Table 4 presents the details. The control mortar mixture used only OPC as binder. Mortar specimens were kept at ambient laboratory conditions [34] for 7, 28 and 90 days.

2.3. Tests conducted

2.3.1. Fresh mortar test

Different ASTM standards were followed to identify the fresh properties of mortar for all mixtures, and the consistency and setting time were determined following ASTM C187 [35] and ASTM C191 [36], respectively.

2.3.2. Hardened mortar test

The influence of replacement with PP, BA and CaCl₂ was investigated by producing mortar cubes (50 × 50 × 50 mm), as shown in Fig. 5. Three specimens were tested to determine the compressive strength at 7, 28 and 90 days. Furthermore, the microscopic analysis and durability indicators of cement mortar should be further investigated.

3. Results and discussion

3.1. Standard consistency

Fresh properties of the studied mortar were measured in accordance with ASTM C187 [35]. Table

Table 2
Physical properties of cement.

Properties	Cement	ASTM Requirements
Density (Kg/m ³)	2960	ASTM C188-87
Fineness (cm ² /gm)	3500	ASTM C150-95 Min. 2800
Vicat set times (hr:min)	2:30	ASTM C150-95
Initial	5:00	≥45 min
Final		
Normal consistency (%)	25.5	—
Mortar Compressive	16.47	ASTM C150-95
Strength (MPa)	29.81	>12
at 3 days	44.03	>19
7 days		—
28 days		

Table 3
Grading size distribution of sand.

Sieve No.	Sieve Opening mm	Percentage of Passing (%)
#30	0.6	98
#40	0.4	70
#50	0.3	25
#100	0.15	0

Fig. 1. Pottery Powder passed through a No. 200 sieve (75 µm).

6 presents the results. The standard consistency of the control mix was equal to 23.5%. The uniform consistency of the trial matrixes was observed during the investigation. The increment amount of PP and BA increased the water demand given that the total powder content cement + PP or BA and w/cm

remained constant for all mixtures. This finding may be related to the high early rate of hydration of pottery, BA and cement. The same conclusion was adopted by other studies [14,16,27,37]. This behaviour is related largely to the smooth surface texture of the PP and BA particles and the delay in the chemical reaction [16].

3.2. Setting time

PP and BA more slowly reacts with water than Portland cement; thus, its use is likely to increase the stiffening times of the mortar, as shown in Table 6 and Fig. 6. The extension in stiffening time is greater at high replacement levels with PP and BA at approximately 14.5% and 13%, respectively, and at normal temperatures (approximately $25^{\circ}\text{C} \pm 2$). Furthermore, the results indicated a possibility of shrinkage specially with the increasing percentage of replacement. Thus, all specimens were loaded at a controlled temperature of 70°F (21°C) and relative humidity of 55%.

Fig. 2. Preparation of pottery powder.

Fig. 3. SEM image of ground of BA [1].

3.3. Compressive strength

The effect of various parameters, such as age and replacement with PP and BA and CaCl_2 solution, on compressive strength are discussed in this section.

At ambient temperature, compressive strength increased with age, as shown in Table 7. The compressive strength of all mixtures at 90 days was slightly higher than/equivalent to that at 28 days. When the cement was replaced with PP and BA, the compressive strength of the mortar was comparably equal to or marginally less than that of the reference mortar mixtures. The compressive strength of the cement mortar decreased with the increase in OPC replacement (up to 14%) with 30% PP in ambient curing conditions at 28 days, as shown in Fig. 7. A

Table 4

Mixture proportions of all mixes with 4% CaCl_2 (kg/m^3).

Mixture ID	Cement	Sand	Water	CaCl_2	PP	BA
Control	740	2035	344.64	14.36	—	—
PP10	666	2035	344.64	14.36	74	—
PP20	592	2035	344.64	14.36	148	—
PP30	518	2035	344.64	14.36	222	—
BA10	666	2035	344.64	14.36	—	74
BA20	592	2035	344.64	14.36	—	148
BA30	518	2035	344.64	14.36	—	222

linear relationship was found between strength increments and PP and BA percentage replacement, as shown in Figs. 7 and 8. This linearity was observed for long curing times, probably due to the high contribution of PP and BA to strength.

An irregular strength increase was shown when the pottery materials were combined with different percentages, at a combination of 5%, 10% and 15% BA and 5%, 10% and 15% PP as an alternative to cement. Fig. 9 illustrates the compressive strength results of mixtures with control mix and combined pottery materials. The combined pottery materials provided nearly equivalent strength to control mixtures in all ages. A portion of the cracks is generated during the load due to the water absorbed from the PP and BA especially with the high percentage of pottery materials at earlier ages. In some cases, the strength increments increased at 90 days (also refer to Table 8). The compressive strength decreased with up to 18% replacement of OPC with 30% BA. With

Fig. 4. Calcium chloride powder and solution.

Table 5

Mixture proportions of all mixes without CaCl_2 (kg/m^3).

Mixture ID	Cement	Sand	Water	PP	BA
Control Mix	740	2035	359	—	—
PP10	666	2035	359	74	—
PP20	592	2035	359	148	—
PP30	518	2035	359	222	—
BA5	703	2035	359	—	37
BA10	666	2035	359	—	74
BA15	629	2035	359	—	111
BA20	592	2035	359	—	148
BA30	518	2035	359	—	222
BA5%					
+PP5%	666	2035	359	37	37
+PP10%	629	2035	359	74	37
+PP15%	592	2035	359	111	37
BA10%					
+PP5%	629	2035	359	37	74
+PP10%	592	2035	359	74	74
+PP15%	555	2035	359	111	74
BA15%					
+PP5%	592	2035	359	37	111
+PP10%	555	2035	359	74	111
+PP15%	518	2035	359	111	111

the addition of 4% CaCl_2 , the compressive strength was slightly improved, as shown in Figs. 10 and 11 and Table 7.

The compressive strength of pottery mortars with 4% CaCl_2 increased by approximately 2.3 and 0.7 times for 10% and 20% PP, respectively. When the cement was replaced with 30% PP, the compressive strength was comparably equal to that of the mixture without CaCl_2 . The compressive strength of BA mixtures with 4% CaCl_2 was equal to that of the

Table 6

Fresh properties of tested mixtures.

Cement replacement, %	Water Content of Normal Consistency, %	Initial Time of Setting, min	Final Time of Setting, min
Standard	23.5	130	192
PP10	23.7	138	210
PP20	24.6	144	216
PP30	24.8	152	220
BA10	23.7	136	201
BA20	24.3	140	212
BA30	24.6	143	217

Fig. 6. Vicat test device.

Fig. 5. Moulds used to preparation mortar specimens.

Table 7
Compressive strength of mortar with 4% CaCl_2 .

Mixture ID	Compressive Strength, MPa		
	7 days	28 days	90 days
Control	27.3	44.3	45.6
PP10	23.4	43.4	44.8
PP20	19.7	42.6	43
PP30	18.2	38.1	39.2
BA10	25.3	43.5	44
BA20	19.6	42.1	42.8
BA30	15.1	37.4	38.2

mixture without CaCl_2 at different ages. The same conclusion was drawn by other studies [16,37–40]. This behaviour attributed to the mechanism of clay swelling. When clay contacts with water, exchangeable cations in the clay interlayer space tend to hydrate, thereby forcing clay layers apart. Swelling can occur via two different regimes, namely, crystalline and osmotic swelling [5,7,28,41–44]. Moreover, the possibility of self-healing phenomena was detected by the identification of 20% BA and 20% PP hydration products in the previous cement cracks after

Fig. 7. Compressive strength of mortars with various replacement of PP.

Fig. 8. Compressive strength of mortars with various replacement of BA.

Fig. 9. Compressive strength of mortars with various replacement of combined pottery materials (PP + BA).

Table 8
Compressive strength with different percentages of PP and BA.

Mixture ID	Compressive Strength (MPa)		
	7 days	28 days	90 days
Control	26.6	44.4	44.6
PP10	22.2	43.3	43.8
PP20	18.8	42.2	42.7
PP30	15	37.9	39
BA5	25.8	43.6	43.8
BA10	24.6	43.3	44
BA15	20.3	42.8	43
BA20	18.7	41.4	42.6
BA30	13.8	36.3	38.2
BA5			
+PP5	24.4	43.3	44
+PP10	20.5	43	43.4
+PP15	18.6	40.1	41.4
BA10			
+PP5	20.3	43	43.3
+PP10	19	42.6	43
+PP15	14.3	38.3	39.3
BA15			
+PP5	19.1	42.7	43.2
+PP10	16.3	38.7	39.8
+PP15	14.4	37.3	39

recovery in air, as also observed in other studies [14,16,24].

4. Conclusions

On the basis of the test results, the following conclusions are drawn:

1. The increase in OPC replacement with PP or BA led to an increment in water required to obtain the standard consistency paste. The penetration time for PP and BA was investigated in this research. The results indicated that the heterogeneous powder rapidly absorbs liquid into the powder due to the high porosity among its particles.
2. The results showed that with an increase in PP and BA, the workability increased.
3. The compressive strength of mortar specimens with 10% replacement of PP or BA is similar to that of the control at ages 7, 28 and 90 days, whereas with 20% replacement, the obtained compressive strength is similar to that of the

Fig. 10. Compressive strength of PP mortars with 4% CaCl₂ at different age.

Fig. 11. Compressive strength of BA mortars with 4% CaCl₂ at different age.

control at ages 28 and 90 days only. The strength gain rate at an early age tended to increase, whereas the long-term gain rate slightly increased with high percentage replacement.

4. The compressive strengths of the third group of mortar were lower than those of the first and second groups. The best compressive strength result of the mortar specimens with different replacement ratios of PP and a constant ratio of BA (5%) is BA5 + PP10. The pottery materials were considered low-cost cementitious powder materials. This powder can be used in construction given that it fits the purpose and is affordable.
5. In the case of 4% CaCl₂, the compressive strength at 90 days was unaffected, nearly similar to that of the reference Portland cement mortar.

References

- [1] S.A. Mangi, M.H.W. Ibrahim, N. Jamaluddin, M.F. Arshad, S.A. Memon, S. Shahidan, et al., Coal bottom ash as a sustainable supplementary cementitious material for the concrete exposed to seawater, in: AIP Conference Proceedings, 2019, p. 020002.
- [2] A. Sivakumar, M. Prakash, Characteristic studies on the mechanical properties of quarry dust addition in conventional concrete, J. Civ. Eng. Construct. Technol. 2 (2011) 218–235.
- [3] A. Muthadhi, V. Dhivya, Investigating strength properties of geopolymer concrete with quarry dust, ACI Mater. J. 114 (2017) 355.
- [4] A. Bouadi, A.A. Bousahla, M.S.A. Houari, H. Heireche, A. Tounsi, A new nonlocal HSDT for analysis of stability of single layer graphene sheet, Adv. Nano Res. 6 (2018) 147–162.
- [5] F. Bourada, A.A. Bousahla, M. Bourada, A. Azzaz, A. Zinata, A. Tounsi, Dynamic investigation of porous functionally graded beam using a sinusoidal shear deformation theory, Wind Struct. 28 (2019) 19–30.

- [6] B. Bakhadda, M.B. Bouiadjra, F. Bourada, A.A. Bousahla, A. Tounsi, S. Mahmoud, Dynamic and bending analysis of carbon nanotube-reinforced composite plates with elastic foundation, *Wind Struct.* 27 (2018) 311–324.
- [7] R. Ilyas, S. Sapuan, M. Ishak, Isolation and characterization of nanocrystalline cellulose from sugar palm fibres (Arenga Pinnata), *Carbohydr. Polym.* 181 (2018) 1038–1051.
- [8] Tayeh B.A., Al Saffar D.M., Aadi A.S., Almeshal I, Sulphate resistance of cement mortar contains glass powder, *J. King Saud Univ. Eng. Sci.* (2019) (in press).
- [9] B.A. Tayeh, M.W. Hasaniyah, A. Zeyad, M.O. Yusuf, Properties of concrete containing recycled seashells as cement partial replacement: a review, *J. Clean. Prod.* (2019) 117723 (in press).
- [10] N.-U. Amin, S. Alam, S. Gul, K. Muhammad, Activation of clay in cement mortar applying mechanical, chemical and thermal techniques, *Adv. Cem. Res.* 24 (2012) 319–324.
- [11] Noor-ul-Amin, Use of clay as a cement replacement in mortar and its chemical activation to reduce the cost and emission of greenhouse gases, *Constr. Build. Mater.* 34 (2012) 381–384.
- [12] M. Morsy, S. Alsayed, M. Aqel, Effect of nano-clay on mechanical properties and microstructure of ordinary Portland cement mortar, *Int. J. Civil Environ. Eng. IJCEE-IJENS* 10 (2010) 23–27.
- [13] Z. Ge, Y. Wang, R. Sun, X. Wu, Y. Guan, Influence of ground waste clay brick on properties of fresh and hardened concrete, *Constr. Build. Mater.* 98 (2015) 128–136.
- [14] M. Rafieizonooz, J. Mirza, M.R. Salim, M.W. Hussin, E. Khankhaje, Investigation of coal bottom ash and fly ash in concrete as replacement for sand and cement, *Constr. Build. Mater.* 116 (2016) 15–24.
- [15] r.S.A. T.P. P sudha, Experimental studies on cement mortar for partial replacement of cement by chemically activated clay, *Int. J. Earth Sci. Eng.* 8 (2015) 2038–2044.
- [16] O.M. Olofinnade, A.N. Ede, J.M. Ndambuki, G.O. Bamigboye, Structural properties of concrete containing ground waste clay brick powder as partial substitute for cement, *Mater. Sci. Forum* (2016) 63–67.
- [17] D.M.A.-R. Al Saffar, Experimental investigation of using ultra-fine glass powder in concrete, *Int. J. Eng. Res. Afr.* 7 (2017) 33–39.
- [18] B.A. Tayeh, M. Al Saffar Doha, Influence of pottery clay in cement mortar and concrete mixture: a review, *Int. J. Eng. Technol.* 7 (2018) 67–71.
- [19] M. Abed, R. Nemes, B.A. Tayeh, Properties of self-compacting high-strength concrete containing multiple use of recycled aggregate, *J. King Saud Univ. Eng. Sci.* (2018) (in press).
- [20] M.M. Khan, S. Panchal, A. Sharma, A.A. Bharti, Innovative use of brick powder and marble dust as a mineral admixture in concrete, *Int. J. Civ. Eng. Technol.* 8 (2017) 987–990.
- [21] M. Bediako, Pozzolanic potentials and hydration behavior of ground waste clay brick obtained from clamp-firing technology, *Case Stud. Construct. Mater.* 8 (2018) 1–7.
- [22] R.A. Ilyas, S.M. Sapuan, R. Ibrahim, H. Abral, M. Ishak, E. Zainudin, et al., Sugar palm (Arenga pinnata (Wurmb.) Merr) cellulosic fibre hierarchy: a comprehensive approach from macro to nano scale, *J. Mater. Res. Technol.* 8 (2019) 2753–2766.
- [23] D. Dobias, P. Pokorny, Influence of partial replacement of hydraulic binder by ground brick on the characteristics of composites, *Proced. Eng.* 190 (2017) 568–574.
- [24] S.A. Mangi, W. Ibrahim, M. Haziman, N. Jamaluddin, M.F. Arshad, S.W. Mudjanarko, Recycling of coal ash in concrete as a partial cementitious resource, *Resources* 8 (2019) 99.
- [25] R. Ilyas, S. Sapuan, M. Ishak, E. Zainudin, Sugar palm nanocrystalline cellulose reinforced sugar palm starch composite: degradation and water-barrier properties, in: *IOP Conference Series: Materials Science and Engineering*, 2018, 012006.
- [26] H. Fourn, H.A. Atmane, M. Bourada, A.A. Bousahla, A. Tounsi, S. Mahmoud, A novel four variable refined plate theory for wave propagation in functionally graded material plates, *Steel Compos. Struct.* 27 (2018) 109–122.
- [27] H. Bellifa, A. Bakora, A. Tounsi, A.A. Bousahla, S. Mahmoud, An efficient and simple four variable refined plate theory for buckling analysis of functionally graded plates, *Steel Compos. Struct.* 25 (2017) 257–270.
- [28] R. Ilyas, S. Sapuan, M.L. Sanyang, M.R. Ishak, E. Zainudin, Nanocrystalline cellulose as reinforcement for polymeric matrix nanocomposites and its potential applications: a review, *Curr. Anal. Chem.* 14 (2018) 203–225.
- [29] R. Ilyas, S. Sapuan, M. Ishak, E. Zainudin, Development and characterization of sugar palm nanocrystalline cellulose reinforced sugar palm starch bionanocomposites, *Carbohydr. Polym.* 202 (2018) 186–202.
- [30] C. ASTM, 150 Standard Specification for Portland Cement, ASTM International, 2017. ICS Number Code.
- [31] www.halliburton.com.
- [32] P. Suraneni, J. Monical, E. Unal, Y. Farnam, J. Weiss, Calcium oxychloride formation potential in cementitious pastes exposed to blends of deicing salt, *ACI Mater. J.* 114 (2017) 631–641.
- [33] A. C109, Standard test method for compressive strength of hydraulic cement mortars using 2-in. Or [50-mm] cube specimens, *Am. Soc. Test. Mater. Stand. Pract.* (2011).
- [34] A. Chikh, A. Tounsi, H. Hebali, S. Mahmoud, Thermal buckling analysis of cross-ply laminated plates using a simplified HSDT, *Smart Struct. Syst.* 19 (2017) 289–297.
- [35] C. ASTM, 187-11. Standard Test Method for Amount of Water Required for Normal Consistency of Hydraulic Cement Paste, ASTM International, West Conshohocken, PA, USA, 2011.
- [36] A.C. 191, Standard Test Method for Time of Setting of Hydraulic Cement by Vicat Needle, *Am. Soc. Test. Mater. Stand. Pract.* (2011).
- [37] Y. Beldjelili, A. Tounsi, S. Mahmoud, Hygro-thermo-mechanical bending of S-FGM plates resting on variable elastic foundations using a four-variable trigonometric plate theory, *Smart Struct. Syst.* 18 (2016) 755–786.
- [38] B.A. Tayeh, D.M. Al Saffar, Utilization of waste iron powder as fine aggregate in cement mortar, *J. Eng. Res. Technol.* 5 (2018).
- [39] F. Bergaya, G. Lagaly, *Handbook of Clay Science*, vol. 5, Newnes, 2013.
- [40] Z. Belabed, A.A. Bousahla, M.S.A. Houari, A. Tounsi, S. Mahmoud, A new 3-unknown hyperbolic shear deformation

- theory for vibration of functionally graded sandwich plate, *Earthquakes Struct* 14 (2018) 103–115.
- [41] R. Anderson, I. Ratcliffe, H. Greenwell, P. Williams, S. Cliffe, P. Coveney, Clay swelling—a challenge in the oilfield, *Earth Sci. Rev.* 98 (2010) 201–216.
- [42] M. Nehdi, Clay in cement-based materials: critical overview of state-of-the-art, *Constr. Build. Mater.* 51 (2014) 372–382.
- [43] L. Yusriah, S. Sapuan, E.S. Zainudin, M. Mariatti, Characterization of physical, mechanical, thermal and morphological properties of agro-waste betel nut (*Areca catechu*) husk fibre, *J. Clean. Prod.* 72 (2014) 174–180.
- [44] R. Ilyas, S. Sapuan, M. Ishak, E. Zainudin, Sugar palm nanofibrillated cellulose (*Arenga pinnata* (Wurmb.) Merr): effect of cycles on their yield, physic-chemical, morphological and thermal behavior, *Int. J. Biol. Macromol.* 123 (2019) 379–388.